



Product data sheet 2000-2-2

Page 1 of 3 / As per: 04-2014

Certification number: 1724 - CPD - 041101



Product trade name: **MONOPLEX SBS PV 250 S5, slated
Elastomer bitumen torch-on membrane**

Product-number: 11956

Product specification: DIN EN 13707

Length, Width: 5.00 m x 1.00 m
Thickness: 5.00 mm
Coating type: Elastomer bitumen
Content of solubility: N/A
Reinforcement: Polyester fleece
Min. weight of reinforcement: 250 g/m²

Polymer bitumen torch-on membrane with polyester fleece reinforcement
– as a top layer of roof insulation

Characteristics according to DIN EN 13 707	Test method/ Classification	Units	Requirements/ Critical value
Visible defects	DIN EN 1850-1	-	no visible defects
Length	DIN EN 1848-1	m	≥ 5.00
Width	DIN EN 1848-1	m	≥ 1.00
Straightness	DIN EN 1848-1	mm/10 m	≤ 20
Mass per unit area	DIN EN 1849-1	kg/m ²	unverifiable result
Thickness	DIN EN 1849-1	mm	5,00 ± 0,2 abs.
Water tightness at 200 kPa test pressure	DIN EN 1928 Method B	-	passed
External fire performance	DIN V ENV 1187	-	see testing of system
Reaction to fire	DIN EN ISO 11925-2	-	Class E according to DIN EN 13501-1
Water tightness after stretching at low temperatures	DIN EN 13897	-	unverifiable result
Peel resistance of joint	DIN EN 12316-1	N/50 mm	unverifiable result

GEORG BÖRNER

Chemisches Werk für Dach- und
Bautenschutz GmbH & Co. KG

Heinrich-Börner-Straße 31
D-36251 Bad Hersfeld

Tel. +49 (0)6621 175-0
Fax +49 (0)6621 175-200

Info@GeorgBoerner.de
www.GeorgBoerner.de

Reserving changes. The indicated technical values refer to the date of production.



Product data sheet 2000-2-2

Page 2 of 3 / As per: 04-2014

Certification number: 1724 - CPD - 041101



Characteristics according to DIN EN 13 707	Test method/ Classification	Units	Requirements/ Critical value
Shear resistance of joint	DIN EN 12317-1	N/50 mm	unverifiable result
Tensile properties: maximum tensile force	DIN EN 12311-1	N/50 mm	1000 / 900 \pm 20 %
Tensile: elongation	DIN EN 12316-1	%	35 / 40 \pm 20 %
Resistance to impact	DIN EN 12691	mm	unverifiable result
Resistance to static loading	DIN EN 12730	kg	unverifiable result
Resistance to tearing (nail shank)	DIN EN 12310-1	N	unverifiable result
Resistance to root penetration	DIN EN 13948	-	-
Dimensional stability	DIN EN 1107-1	%	-
Form stability under cyclic temperature change	DIN EN 1108	%	unverifiable result
Flexibility at low temperatures	DIN EN 1109	°C	\leq - 15
Flow resistance at elevated temperatures	DIN EN 1110	°C	\geq + 100
Artificial aging DIN EN 1296	DIN EN 1109	°C	unverifiable result
	or DIN EN 1110	°C	unverifiable result
Adhesion of granules	DIN EN 12039	%	-
Water vapour transmission properties	DIN EN 1931	-	-

Customer information:

Purpose:

MONOPLEX SBS PV 250 S5 is a polymer bitumen torch-on membrane. In the build up of the flat roof layers this membrane is used as a waterproof layer on any angle and together with other polymer bitumen membranes or bitumen underlay membranes it is used as a top layer of roof insulation.

Please pay attention to the inclination and operational demands!

GEORG BÖRNER

Chemisches Werk für Dach- und
Bautenschutz GmbH & Co. KG

Heinrich-Börner-Straße 31
D-36251 Bad Hersfeld

Tel. +49 (0)6621 175-0
Fax +49 (0)6621 175-200

Info@GeorgBoerner.de
www.GeorgBoerner.de

Reserving changes. The indicated technical values refer to the date of production.



Product data sheet 2000-2-2

Page 3 of 3 / As per: 04-2014

Certification number: 1724 - CPD - 041101



Application:

The application of **MONOPLEX SBS PV 250 S5** is carried out in accordance with the nationally valid regulations for roofs with sealants. The whole membrane is torched-on with a joint overlap of at least 8 cm. In case of a directly mechanically fixing the joint overlap has to be approximately 12 cm.

Advise:

Due to its thermoplastic inlay the membrane must not be overheated.

Loose laying or mechanical fixing of the membrane as well as spots or stripes of heating/adhesion on the surface followed by heating/adhesion of the joint overlaps can cause corrugation if the outside temperature and/or surface temperature are too low.

Please note that the colour of the granules can vary during their useful life due to the effects of weather and other outside circumstances.

Chemical resistance:

MONOPLEX SBS PV 250 S5 is water-resistant as well as resistant to watery solutions of salt, diluted non oxidising acids and bases. Aliphatic and aromatic hydrocarbons as well as chlorine hydrocarbons, oils and greases loosen **MONOPLEX SBS PV 250 S5**.

Storage:

Store upright in a cool and dry place.

Safety data sheet:

Supplementary safety data sheet is available on request.

GEORG BÖRNER

Chemisches Werk für Dach- und
Bautenschutz GmbH & Co. KG

Heinrich-Börner-Straße 31
D-36251 Bad Hersfeld

Tel. +49 (0)6621 175-0
Fax +49 (0)6621 175-200

Info@GeorgBoerner.de
www.GeorgBoerner.de

Reserving changes. The indicated technical values refer to the date of production.